



## C-Series Sodium Alginate

Product	Viscosity* (cps)	Particle Size	Moisture	pH (1% solution)	Water Solubility	Hydration Time	Appearance	Standard Packaging
S-15-C	10 - 50	96% < 25 mesh	15% max	6.0-8.5	excellent in hot and cold water	20 min	granular powder	valve packed bags, fiber drums, super sacks
S-50-C	50-150							
S-160-C	150-300							
S-500-C	300-600							
S-1300-C	600-900							

\* 1% solution @25 °C, #3 spindle, 10 RPM, Brookfield RVT



## QD-Series Sodium Alginate (quick dispersing)

Product	Viscosity* (cps)	Particle Size	Moisture	pH (1% solution)	Water Solubility	Hydration Time	Appearance	Standard Packaging
S-15-QD	10 - 50	96% < 25 mesh	15% max	6.0-8.5	excellent in hot and cold water	20 min	granular powder	valve packed bags, fiber drums, super sacks
S-50-QD	50-150							
S-160-QD	150-300							
S-500-QD	300-600							
S-1300-QD	600-900							

\* 1% solution @25 °C, #3 spindle, 10 RPM, Brookfield RVT



## QS-Series Sodium Alginate (quick soluble)

Product	Viscosity* (cps)	Particle Size	Moisture	pH (1% solution)	Water Solubility	Hydration Time	Appearance	Standard Packaging
S-15-QS	10 - 50	96% < 25 mesh	15% max	6.0-8.5	excellent in hot and cold water	< 10 min	granular powder	valve packed bags, fiber drums, super sacks
S-50-QS	50-150							
S-160-QS	150-300							
S-500-QS	300-600							
S-1300-QS	600-900							

\* 1% solution @25 °C, #3 spindle, 10 RPM, Brookfield RVT



## N-Series Sodium Alginate

Product	Viscosity (cps)	Particle Size	Moisture	pH (1% solution)	Water Solubility	Hydration Time	Appearance	Standard Packaging
S-500-N	300-500*	96% < 25 mesh	15% max	6.0-8.5	excellent in hot and cold water	20 min	granular powder	valve packed bags, fiber drums, super sacks
S-1300-N	600-900**							

\* 1% solution @25 °C, #2 spindle, 60 RPM, Brookfield RVT

\*\* 1% solution @25 °C, #3 spindle, 10 RPM, Brookfield RVT