

SNP  **Polyurethane Dispersions (PUDs)** *SNP's most popular PUDs listed, others are available.*

Product	NMP Free	Co-Solvent Free	Solids (%)	VOC (g/L)	Sward Hardness (D-2134)	Gloss	Tensile Strength psi (D-882)	% Elongation (D-882)
S-1401-L	YES	NO	31-33	84-90	46	80-100	7,000	60
S-1403-L	YES	NO	34-36	111-113	32	80-100	6,200	420
S-1414-L	YES	NO	34-36	100-120	32	80-100	6,200	420
S-1428-L	YES	NO	31-33	53-55	6	70-90	4,350	800
S-1442-L	YES	NO	31-33	102-104	32	80-100	3,000	50
S-1453-L	YES	NO	31-33	55-60	2	80-100	3,850	1,000
S-1455-L	YES	NO	31-33	101-102	10	80-100	3,000	400
S-1408-L	NO	YES	34-36	1.8-2.1	22	70-100	3,200	450
S-1409-L	NO	YES	34-36	1.8-2.1	20	70-100	4,300	400
S-1416-L	NO	YES	34-36	2.2-2.6	22	70-100	3,300	170
S-1432-L	NO	YES	36-38	10-20	24	70-100	4,840	331
S-1434-L	NO	YES	34-36	13-14	15	70-100	4,510	919
S-1436-L	NO	YES	50-55	10-12	5	30-90	2,410	2,070
S-1440-L	NO	YES	32.5-34.5	6.2-6.5	N/A	<5	1,590	512